

EGGAR&CO(Chemicals)Ltd

High Street
Theale
Reading
RG7 5AR



Tel: 0118 930 2379 Fax: 0118 932 3224
Email: sales@eggar.co.uk Web: www.eggar.co.uk

13i

Technical Specification

PARAFFIN WAX 5544

Congealing Point, °C	ASTM D 938	58.0 – 63.0
Oil Content, %	ASTM D 721	0.00 – 3.00
Needle Penetration at 25 °C, dmm	ASTM D 1321	18 – 22
Colour-Saybolt, kA	ASTM D 156	26 - 30

For and on behalf of EGGAR & Co (Chemicals) Limited
This certificate has been generated electronically and is valid unsigned
John Gibbins (Director)

Issued:- 16 April 2008

