



## Technical Specification

### LIQUID PARAFFIN WAX 5783

PARAMETER, UNIT	METHOD	SPECIFICATION
CONGEALING POINT, °C	ASTM D 938	54.0 – 56.0
OIL CONTENT, wt %	ASTM D 721	0.00 – 0.50
NEEDLE PENETRATION at 25 °C, dmm	ASTM D 1321	16 – 20
COLOUR SAYBOLT, k.A.	ASTM D 156	29 – 30

#### PURITY

BfR XXV. (Hard Paraffins, Micros.etc)  
FDA CFR 21 § 172.886 (Petroleum wax)  
Dutch Warenwet

Paraffin 5783 is recognised as safe in food contact applications and for pharmaceutical and cosmetics formulations.

For and on behalf of EGGAR & Co (Chemicals) Limited  
This certificate has been generated electronically and is valid unsigned  
John Gibbins (Director)

Issued:- 16 April 2008