

EGGAR&CO(Chemicals)Ltd

High Street
Theale
Reading
RG7 5AR



Tel: 0118 930 2379 Fax: 0118 932 3224
Email: sales@eggar.co.uk Web: www.eggar.co.uk

13i

Technical Specification

PARAFFIN WAX 8110

Congealing Point, °C	ASTM D 938	62.0 - 64.0
Penetration at 25 °C, dmm	ASTM D 1321	12 - 14
Colour, Saybolt	ASTM D 156	22 - 30

For and on behalf of EGGAR & Co (Chemicals) Limited
This certificate has been generated electronically and is valid unsigned
John Gibbins (Director)
Issued:- 16 April 2008

Every care has been taken to compile this information accurately. In view of the fact that the application of this information is outside our control, we disclaim any liability incurred in connection with its application or use.