



High Street  
Theale

Reading  
RG7 5AR

Tel: 0118 930 2379 Fax: 0118 932 3224  
Email: sales@eggar.co.uk Web: www.eggar.co.uk

13i

## Technical Specification

FOR: "EASTMAN" Cellulose Acetate (PM 4971) (CA-394-60S)	SPECIFICATION NO.: 4971-1
	PAGE: 1 of 1
	EFFECTIVE DATE:

### A. GENERAL

**Changes to Document:** This is a new document per MOC 2002-1047-01478.

A-1. This specification describes one type of "EASTMAN" Cellulose Acetate unfiltered, pelleted esters which are used in applications related to the castings, coatings, filter tow, or membrane fields which must meet each of the requirements listed in Section B when tested as directed by the referenced methods.

A-2. Material Safety Data Sheet 150000001237 outlines the safety precautions for Eastman® Cellulose Acetate.

### B. PROPERTIES AND TEST METHODS

Properties	Limits	Test Methods
B-1. ASTM-A Viscosity, sec	24 - 44	TECE-A-CL-G-V-23
B-2. Acetyl, wt%	40.0 ± 0.5	TECE-A-CL-G-POT-60
B-3. Moisture, wt%	5.0 (max)	TECE-A-CL-G-GA-8

For and on behalf of EGGAR & Co (Chemicals) Limited  
This certificate has been generated electronically and is valid unsigned  
John Gibbins (Director)

Issued:- 16 April 2008

Every care has been taken to compile this information accurately. In view of the fact that the application of this information is outside our control, we disclaim any liability incurred in connection with its application or use.