



High Street
Theale

Reading
RG7 5AR

Tel: 0118 930 2379 Fax: 0118 932 3224
Email: sales@eggarr.co.uk Web: www.eggarr.co.uk

13i

Technical Specification

| | |
|---|---------------------------|
| FOR: "EASTMAN" Cellulose Acetate (CA-398-6) (PM 1849) | SPECIFICATION NO.: 1849-9 |
| | PAGE: 1 of 1 |
| | EFFECTIVE DATE: 03/11/04 |

A. GENERAL

- A-1. This specification describes one type of "EASTMAN" Cellulose Acetate filtered powder which is used in applications related to the coatings, photographic film, plastic, or membrane fields and must meet each of the requirements listed in Section B when tested as directed by the referenced methods.
- A-2. Material Safety Data Sheet 100000477 outlines the safety precautions for "EASTMAN" Cellulose Acetate.

B. PROPERTIES AND TEST METHODS

| Properties | Limits | Test Methods |
|-------------------------------|------------|--------------------|
| B-1. ASTM-A Viscosity, sec | 5.0 - 7.0 | TECE-A-CL-G-V-3 |
| B-2. Acetyl by Titration, wt% | 39.8 ± 0.5 | TECE-A-CL-G-POT-60 |
| B-3. Moisture, wt% | 3.0 (max) | TECE-A-CL-G-GA-55 |

For and on behalf of EGGAR & Co (Chemicals) Limited
This certificate has been generated electronically and is valid unsigned
John Gibbins (Director)

Issued:- 16 April 2008

Every care has been taken to compile this information accurately. In view of the fact that the application of this information is outside our control, we disclaim any liability incurred in connection with its application or use.