



## Technical Specification

### CAB 531-1

**CODE  
DESIGNATION:**

<b>CAB</b>	-	<b>53</b>		<b>1</b>	-	<b>1</b>
Cellulose Acetate Butyrate		ApproxButryl Content at the Triester(Wt %)		No of OH groups per each Four Anhydroglucose unit.		Falling-Ball Viscosity, (secs)

Viscosity (secs)	ASTM D 817(Formula A)section 57-58. and ASTM D 1343	1.3 -2.6
Acetyl Content, wt %	ASTM D 817 section 13-28	2 - 4
Butyryl Content, wt %	ASTM D 817 section 13-28	48 - 52
Free Acidity, % as Acetic Acid	ASTM D 817 section 8-12	0.03 max
Moisture content(packaged) %	ASTM D 817 section 4-5	3.0 max
Colour		White
Form		Powder

For and on behalf of EGGAR & Co (Chemicals) Limited  
This certificate has been generated electronically and is valid unsigned  
John Gibbins (Director)

Issued:- 16 April 2008

Every care has been taken to compile this information accurately. In view of the fact that the application of this information is outside our control, we disclaim any liability incurred in connection with its application or use.