



Sales Specification

Product: *EPOLENE* E-20 Wax

Specification: E-20

Effective Date: 25-Apr-02

Version: 8

Pages: 1 of 1

A. GENERAL

A-1 This specification replaces Sales Specification E-20-7, dated November, 2000. No changes have been made to the properties and test method section.

A-2 This specification describes a grade of *EPOLENE* Wax that meets all of the requirements listed in Section B when tested as directed by the referenced methods.

B. PROPERTIES AND TEST METHODS

	<u>Property</u>	<u>Specification Limits</u>	<u>Test Method</u>
B-1	Softening Point, °C	106.0 - 114.0	542-112
B-2	Acid Number, mg-KOH	14.0 - 18.5	542-110
B-3	Viscosity @ 125C, CPS	1000 - 2000	542-111
B-4	Color, Gardnr	2.0 MAX	542-130
B-5	Cationic Emulsion E-20, %T	50.0 MIN	542-106

For reasons of safety and accuracy, the person performing methods described herein must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers.

Texas Eastman Division
Eastman Chemical Company
Longview, TX 75607