



Sales Specification

Product: *EPOLENE* E-43 Wax

Specification: E-43
Effective Date: 01-Jan-01
Version: 7
Pages: 1 of 1

A. GENERAL

- A-1 This specification replaces Sales Specification E-43-6. The specification has had no changes made to the tests, limits, or test methods.
- A-2 This specification describes a grade of EPOLENE Wax that meets all of the requirements listed in Section B when tested as directed by the referenced methods.

B. PROPERTIES AND TEST METHODS

	<u>Property</u>	<u>Specification Limits</u>	<u>Test Method</u>
B-1	Acid Number, mg-KOH	40.0 - 55.0	542-110
B-2	Softening Point, °C	153.0 - 162.0	542-112
B-3	Color, Gardnr	11.0 MAX	542-130
B-4	Viscosity @ 190C, CPS	150 - 700.	542-111
B-5	High Pressure Emulsion, %T	50 MIN	542-102A

For reasons of safety and accuracy, the person performing methods described herein must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers.

Texas Eastman Division
Eastman Chemical Company
Longview, TX 75607